

01561 Lampertswalde/Dresden Tel. +49 3522 33-30 · Fax +49 3522 33-399  $www.krono\text{-}original.com \cdot info@kronoflooring.com$ 

## **Technical Datasheet Titan Prestige**

Made by Kronospan

Direct Pressure Laminate, Level of use according to EN 13329: class 23/33 - AC5









| * Land to the state of the stat |
|--|
| protects the HEALTH  |

## DIMENSION

| BINIENGIGIA         |               |                                       |            |             | HEALTH   |
|---------------------|---------------|---------------------------------------|------------|-------------|--|
| dimension           | thickness (d) | 14 ± 0,50 mm · dmax - dmin ≤ 0,50 mm  |            |             | ÉMISSIONS DANS L'AIR INTÉRIEUR   |
| length              |               | 1285 ± 0,50 mm                        |            |             | <b> </b>   |
|                     | width (b)     | 157 ± 0,10 mm · bmax - bmin ≤ 0,20 mm |            |             | A+ A B C   |
| profile             | long side     | twin clic                             | short side | drop loc    | EN 14041:2004/AC:2006; Cfl-s1; E1; DS; PCP < 5ppm,<br>Bodenbeläge für die Verwendung in Gebäuden,<br>For internal use as floor coverings (see EN 14041),<br>DOP: LW0022016/N8 0766; N8 0767; |
| groove              | long side     | real groove                           | short side | real groove | Kronoflooring GmbH, Mühlbacher Str. 1, 01561 Lampertswalde, Germany, www.krono-original.com/en/guarantee   |
| TOLERANCE           |               |                                       |            |             |  |
| squareness EN 13329 |               |                                       | ≤ 0,20 mm  |             |  |
|                     |               |                                       |            |             |  |

| TOLERANCE   |             |            |   |  |
|---|-------------|------------|---|--|
| squareness  |             | EN 13329   | ≤ 0,20 mm   |  |
| straightness  |             | EN 13329   | ≤ 0,30 mm   |  |
| flatness crosswise  |             | EN 13329   | concave: ≤ 0,15% · convex: ≤ 0,20%                          |  |
| flatness length   |             | EN 13329   | concave: ≤ 0,50% · convex: ≤ 1,00%                          |  |
| gaps between elements                                     |             | EN 13329   | average: ≤ 0,15 mm · max: ≤ 0,20 mm                         |  |
| height difference between elements                        |             | EN 13329   | average: ≤ 0,10 mm · max: ≤ 0,15 mm                         |  |
| misalignment  |             |            | ± 2 mm  |  |
| TEST  |             |            |   |  |
| abrasion resistance                                       |             | EN 13329   | AC5 (≥ 6000 rpm)  |  |
| impact resistance   |             | EN 13329   | small ball ≥ 15 N · big ball ≥1000 mm                       |  |
| micro scratch resistance                                  |             | EN 13329   | ≤ MSR-B2  |  |
| stain resistance  | group 1 & 2 | EN 13329   | grade 5   |  |
|   | group 3     | EN 13329   | ≥ grade 4   |  |
| castor chair test   |             | EN 13329   | no change in appearance or damage,<br>as defined per EN 425 |  |
| effect of a furniture leg                                 |             | EN 13329   | no damage shall be visible, when testet with foot type 0    |  |
| thickness swelling  |             | EN 13329   | ≤ 15%   |  |
| static indentation  |             | EN 13329   | ≤ 0,05 mm   |  |
| light fastness  |             | EN 13329   | grey scale ≥ 4 at blue wool grade 6                         |  |
| dimensional variations after changes in relative humidity |             | EN 13329   | lengthwise ≤ 0,9 mm · crosswise ≤ 0,9 mm                    |  |
| locking strength  |             | EN 13329   | length ≥ 1 kN/m · width ≥ 2 kN/m                            |  |
| surface soundness   |             | EN 13329   | ≥ 1,25 N/mm²  |  |
| ENVIRONMENT   |             |            |   |  |
| emission of formaldehyde                                  |             | EN 717-1   | Klasse E1   |  |
| PHYSICAL BEHAVIOR   |             |            |   |  |
| fire behavior   |             | EN 13501-1 | Cfl s1  |  |
| slide resistance  |             | EN 13893   | technical class DS  |  |
| thermal resistance  |             | EN 12667   | 0,108 (m <sup>2</sup> K)/W ± 15%                            |  |

| PHYSICAL BEHAVIOR        |          |                                  |  |  |  |  |
|--------------------------|----------|----------------------------------|--|--|--|--|
| fire behavior EN 13501-1 |          | Cfl s1                           |  |  |  |  |
| slide resistance         | EN 13893 | technical class DS               |  |  |  |  |
| thermal resistance       | EN 12667 | 0,108 (m <sup>2</sup> K)/W ± 15% |  |  |  |  |
| thermal conductivity     | EN 12664 | 0,126 W/(m*K) ± 15%              |  |  |  |  |
| antistatic behavior      | EN 1815  | body voltage ≤ 2kV               |  |  |  |  |

<sup>\*</sup>Detailed warranty conditions are available at www. krono-original.com

For further information, please see: www.blauer-engel.de